

# ZERO<sup>®</sup>

No crimp, unidirectional fabric:

- Direct translation of properties
  - Highly efficient and very affordable
- 

## UNI-Q-22.3-SM

**Fabric: Unidirectional**

**Raw Material:** Uni – T-700 SC 24K 50C (Toray) – 97% of weight

Hot Melt Stabilizing Yarns on back of fabric – 3% of weight

**Link to carbon fiber datasheet:** <https://www.toraycma.com/page.php?id=661>

**Fabric Width:** 12"

**Braid Angle:** 0°

**Braid Yield:** 4.3 ft/lb (22.3 m/kg)

**Areal Weight:** 756 GSM

**Layer Thickness (@55%FV):** .030" (.76 mm)


**Standard Fabric Tolerances**

**Yield Tolerance:** +/- 5%

**Angle Tolerance:** +/- 3°

Standard Packaging on 6" Cores

*Additional Quality Specifications available upon request*



---

For more information, please visit [www.braider.com](http://www.braider.com), or contact a sales representative at [sales@braider.com](mailto:sales@braider.com) or 513-688-3200

---

All technical information and data contained herein is believed accurate and reliable. However, the accuracy and completeness of this information is not guaranteed and is subject to change without notice. A&P Technology shall not be liable for injury, loss or damage whether direct or consequential arising out of use of the data provided herein.